

MICROGRAVITY SCIENCES AND PROCESSES SYMPOSIUM (A2)  
Fluid and Materials Sciences (2)

Author: Prof. Shinichi Yoda  
Japan Aerospace Exploration Agency (JAXA), Japan, yoda.shinichi@jaxa.jp

## GLASS FORMATION OF OXIDE SYSTEM BY CONTAINERLESS PROCESSING AND LARGE SIZE APPLICATION

**Abstract**

The containerless processing is a unique method to create new glasses, because it suppresses nucleation at the interface between liquid and crucible during solidification and it enables molten samples to be solidified without crystallization by forming free interface. Using containerless processing with an aerodynamic levitation furnace,  $\text{LaO}_3/2\text{TiO}_2$  binary and  $\text{LaO}_3/2\text{TiO}_2\text{ZrO}_2$  ternary glasses were synthesized in bulk form. First, based on the starting compound of  $\text{La}_4\text{Ti}_9\text{O}_{24}$ ,  $\text{LaO}_3/2\text{TiO}_2$  system was investigated. Secondly, from the following three aspects; (i) enhancement of glass forming ability, (ii) maintaining high refractive index  $n_d$ , and (iii) widening the Abbe number  $d$  that varies with compositions of glasses,  $\text{ZrO}_2$  was selected as the third component with La-Ti-O system. As for (i), large single bonding strength of ZrO connection is appropriate for building/ connecting glass-network. Besides, ion binding ratio in ZrO is suitable for network formation. As for (ii), molar refractive index  $R_m$  and molar volume  $V_m$  of each cation  $\text{La}^{3+}$ ,  $\text{Ti}^{4+}$ ,  $\text{Zr}^{4+}$  that affects the glass property,  $\text{ZrO}_2$  addition does not decrease  $n_d$ . As for (iii), inherent wavelength  $\lambda_0$  of  $\text{Zr}^{4+}$  was expected for increasing Abbe Number. The glass transition temperature  $T_g$  and the crystallization onset temperature  $T_x$  of the obtained glasses were determined by differential scanning calorimetry. The thermal stability was evaluated by  $T ( =T_x - T_g )$ . By comparing values of  $T$  and glass-forming region in binary glass with those of ternary glass system,  $\text{ZrO}_2$  substitution was found to be effective for stabilizing the vitrification. The wavelength dispersion of the refractive indices was measured by spectroscopic ellipsometry. It was found that these glasses had outstandingly high refractive indices over 2.26 in  $n_d$ . In addition, they were colorless and transparent, which means promising candidate for new optics materials. The high refractive index  $n_d$  of these glasses was due to their closed oxygen packing densities. Wider range of Abbe number  $d$  was achieved in  $\text{LaO}_3/2\text{TiO}_2\text{ZrO}_2$  ternary glass by expanding the glass forming region compared to that of  $\text{LaO}_3/2\text{TiO}_2$  binary glass. The inherent absorption wavelength  $\lambda_0$  of  $\text{Ti}^{4+}$  played the dominant role in shifting the Abbe number  $d$  in ternary system that nine times wider than that of binary system. Large size diameter glass materials will be also reported by using unique technology.