

MATERIALS AND STRUCTURES SYMPOSIUM (C2)
New Materials and Structural Concepts (4)

Author: Dr. Dafang Zhao

Chinese Academy of Equipment Command and Technology, China, dafang503@hotmail.com

A NEW SINTERING METHOD FOR ULTRA-HIGH-TEMPERATURE RESISTANT SI-AL-C FIBERS

Abstract

Polymer-derived SiC fiber is one of the most important reinforcing materials for high performance ceramic matrix composites (CMC). Ultra-high-temperature performance requirement is keeping proposed for CMC reinforcements with the development of aerospace technology. Among the strategies for improving the high-temperature performance, the most accessible method is to prepare near-stoichiometric SiC fiber by introducing small amount of aluminum (Si-Al-C fiber) through ultra-high-temperature sintering. Si-Al-C fibers show an excellent thermal stability up to 1900 degree C, a good oxidation resistance, an excellent chemical corrosion resistance and creep resistance. Commonly, the Si-Al-C fibers were derived from polyaluminocarbosilane (PACS). PACS was melt-spun, and the spun fibers were cured in the air where oxygen was introduced to the fibers. The cured fibers were pyrolyzed in inert gas up to 1300 degree C to get Si-Al-C-O fibers, which contains non-stoichiometric excess of carbon and oxygen. The Si-Al-C fibers were obtained by sintering Si-Al-C-O fibers at 1800 degree C in Ar. But, the oxygen content should be controlled strictly to get a desirable fiber in the method. In our work, a new sintering method was designed and studies. It demands lower oxygen content for cured PACS fiber. In addition, it can control decomposition of SiC_xO_y phase and densification process. The sintering method can be interpreted as follows: a cured PACS fiber was continuously pyrolyzed at the range of 1500-1600 degree C, where SiC_xO_y phase decomposed slowly; The obtained fiber was continuously sintered at about 1800 degree C where the fiber can be densified. The SA type SiC fiber prepared this way can avoid grain coarsening with good reproducibility. The strength reservation of the obtained fiber is 77% after been heated at 1800 degree C for 1hr in Ar.